



**AJ-43
TECHNICAL DATA SHEET**

<u>PHYSICAL PROPERTIES</u>	<u>TEST METHOD</u>	<u>TYPICAL RESULTS</u>
DENSITY lb/ft ³	ASTM D 3574	9 +/- 2
HARDNESS DURO SHORE 00	ASTM D 2240	60 +/-5
COMPRESSION DEFLECTION (25%) psi	ASTM D 1056	9 – 13
COMPRESSION SET (%)	ASTM D 1056	20 – 30 %
TENSILE STRENGTH psi	ASTM D 412 (DIE A)	100
TEAR STRENGTH lb/in	ASTM D 624 (DIE C)	18
ELONGATION (%)	ASTM D 412 (DIE A)	150%
RESILIENCE (%)	ASTM D 2632	35 %
SERVICE TEMP. (°F) Low High	ASTM D 746	- 40 200
WATER ABSORPTION Max. Weight change (%)	ASTM D 1056	< 5 %
ACCELERATED AGING [7 Days at 70°C (73.4°F)] Flexibility (180° bend no cracking) Appearance change Change in Compression Deflection (%)	ASTM D 1056	PASS NONE +/- 30%
COMBUSTION CHARACTERISTICS	FMVSS-302 UL94HF-1	PASS PASS Thickness greater than 3/16" only

RESISTANCE TO :

Acid	Excellent
Alkali	Excellent
Gasoline & Oil	Good
Aromatic Hydrocarbons	Fair
Keytones	Fair
Chlorinated Solvents	Poor
Oxidation	Excellent
Ozone	Excellent

AJ43 IS A CLOSED CELL NEOPRENE SPONGE

Ethylene Propylene-Neoprene-SBR

GRADE : SCE-43

ASTM D 1056 designation : 2A3

SAE J 18 APR2002 designation : 2A3

MIL R 6130 designation : II-A/B Medium

The above data represents typical values encountered during normal production runs. This data is not offered as an exact or guaranteed product specification – the user must determine the suitability of the product for his own needs. A.J. Rubber & Sponge Ltd. cannot be held responsible for the inappropriate use or misuse of its products.